

Applicant: Kidsworld Co Ltd
30 Cay Da St, Cay Da Hamlet, Tan Phu Trung Village, Cu Chi District
Ho Chi Minh

Sample description:

Two (02) pieces of submitted sample said to be:

Sample description : **Wax**
Labeled age group : 2+
Factory name : Kidsworld Co Ltd
30 Cay Da St, Cay Da Hamlet, Tan Phu Trung Village, Cu Chi District
Ho Chi Minh
Buyer name : Quins Group Pty Ltd, 95 Wright St, Sunshine VIC 3020, Australia
Country of origin : Vietnam
Country of destination : Australia
Date sample received : November 20, 2020
Date test started : November 20, 2020

Tests conducted: As requested by the applicant, please refer to attached page(s) for details.

Conclusion:

<u>Tested sample</u>	<u>Standard</u>	<u>Result</u>
Tested components of submitted sample	International Standard ISO 8124-3 : 2010 (incorporating Amendment 1 : 2014) -Toxic elements test	Pass

To be continued

For and on behalf of
Intertek Vietnam LTD



LIEM MAI
Hardlines Manager

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)



Test Conducted

1. Toxic Elements Analysis

Test method: International Standard ISO 8124-3: 2010 (incorporating Amendment 1 : 2014), acid extraction method was used and toxic elements content were determined by Inductively Coupled Argon Plasma Spectrometry.

<u>Test item</u>	<u>Result (mg/kg)</u>	<u>Maximum Permissible level (mg/kg)</u>
	(1)	
Soluble Lead (Pb)	< 5	90
Soluble Cadmium (Cd)	< 5	75
Soluble Chromium (Cr)	< 5	60
Soluble Barium (Ba)	< 5	1000
Soluble Antimony (Sb)	< 5	60
Soluble Arsenic (As)	< 2.5	25
Soluble Mercury (Hg)	< 5	60
Soluble Selenium (Se)	< 5	500


Tested component:

(1) Wax: off-white paste

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)



Photo of the Submitted Sample



END OF THE TEST REPORT

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>.

(THIS REPORT SHALL NOT BE REPRODUCED WHOLLY OR IN PARTS WITHOUT WRITTEN APPROVAL FROM THE LABORATORY)

